



**modu
lyss®**

BLAZE 553_961

50

BLAZE


163



LRV 9 L 36 270



LRV 5 L 25 399



LRV 5 L 24 831



LRV 6 L 30 668



LRV 6 L 27 553



LRV 8 L 33 963



LRV 6 L 29 990



LRV 8 L 33 961



LRV 10 L 37 907

BLAZE

164 Technical datasheet

CONSTRUCTION	Minituft® 5/64" loop	FIRE RESISTANCE	EN 13501-1 C _f s1
PILE MATERIAL	100% ECONYL® yarn, 100% Regenerated Solution Dyed Nylon	FASTNESS TO LIGHT	ISO 105-B02 ≥ 7
SECONDARY BACKING	Back2Back: Modified bitumen enhanced with a thermoplastic elastomer, reinforced with a glass fibre fleece covered with 100% PES fleece. 10% recycled content included	RUBBING FASTNESS	EN ISO 105-X12 ≥ 4-5
TOTAL WEIGHT	Ca. 4 950 g/m ²	COLOUR FASTNESS TO WATER	EN ISO 105-E01 ≥ 4-5
PILE WEIGHT	Ca. 640 g/m ²	THERMAL RESISTANCE	ISO 8302 0,040 m ² K/W
PILE ABOVE BACKING	Ca. 215 g/m ²	IMPACT NOISE RATING	ISO 10140 ΔL _w : 9 dB (1 000 Hz) ΔL _w : 15 dB
TOTAL HEIGHT	Ca. 6,1 mm	SOUND ABSORPTION	ISO 354 α _w : 0,15 Hz 125 250 500 1000 2000 4000 α _s 0,00 0,03 0,04 0,12 0,21 0,30
PILE HEIGHT	Ca. 1,0 mm	PERMANENT ANTISTATIC	ISO 6356 ≤ 2 kV
PILE DENSITY	Ca. 0,215 g/cm ³	TRANSVERSAL RESISTANCE	ISO/DIS 10965 ≤ 1 x 10 ⁴ Ohm
TUFT DENSITY	Ca. 200 000 /m ²	SIZE & PACKING	50 cm x 50 cm box: 5 m ² pallet: 20 boxes
CLASSIFICATION	EN 1307 33 - LC1	NUMBER OF COLOURS	9
CASTOR CHAIR SUITABILITY	EN 985 A: continuous use	DIMENSIONAL STABILITY	EN 986 Max. 0,2%
DONNÉES ENVIRONNEMENTALES	Démarche HQE®: cf. FDES suivant NF P01-010 Déclaration du 30/07/2003	GUT-NR LEED®	237E20BA Product contributes toward satisfying Credits under LEED®. For more information, see the modulys sustainable datasheets.

