

Meteor 55-70

TECHNICAL DATA

TECHNICAL DATA	STANDARD	METEOR 55	METEOR 70
CLASSIFICATION			
Classification	EN ISO 10582	Heterogeneous compact floor covering based on polyvinyl chloride	Heterogeneous compact floor covering based on polyvinyl chloride
	EN ISO 10874	Commercial: 33 Industrial: 42	Commercial: 34 Industrial: 43
Wear layer binder content	EN ISO 10582	Type I	Type I
TECHNICAL CHARACTERISTICS			
Total thickness	EN ISO 24346	2.0 mm	2.0 mm
Total weight	ISO 23997	2300 g/m ²	2650 g/m ²
Wear layer thickness	EN ISO 24340	0.55 mm	0.70 mm
Surface treatment		Top Clean™	Top Clean™
Form of delivery	EN ISO 24341 Sheet	approx. 25 running metres x 200 cm Art. no. 25106 ___ 3 digit colour number	approx. 25 running metres x 200 cm Art. no. 25104 ___ 3 digit colour number
		approx. 25 running metres x 400 cm Art. no. 25105 ___ 3 digit colour number	approx. 25 running metres x 400 cm Art. no. 25103 ___ 3 digit colour number
PERFORMANCES FOR CE MARKING REQUIREMENTS (EN 14041)			
Declaration of Performance	EN 14041	0132-0062-DoP-2016-01	0132-0061-DoP-2016-01
Reaction to fire	EN ISO 13501-1	≤0,10mm	≤0,10mm
Electrostatic properties	EN 1815	< 2.0 kV on concrete	< 2.0 kV on concrete
	EN 1081	R1 > 10 ¹⁰ Ω	R1 > 10 ¹⁰ Ω
Thermal resistance	EN ISO 10456	0.02 m ² K/W	0.02 m ² K/W
Slip resistance	EN 13893	μ ≥ 0.3	μ ≥ 0.3
TECHNICAL PERFORMANCES			
Residual indentation	EN ISO 24343-1	Required value: ≤ 0.10 mm	Required value: ≤ 0.10 mm
		Best measured value*: 0.05 mm	Best measured value*: 0.04 mm
Impact sound reduction	EN ISO 717/2 NF S31-074	13dB	7dB
		Class B	Class B
Slip resistance ⁽¹⁾	DIN 51130	R10	R10
Furniture leg	EN 424	No damage	No damage
Castor chair	ISO 4918	No damage	No damage
Curl resistant to heat	EN ISO 23999	≤ 8 mm	≤ 8 mm
Light fastness	EN ISO 105-B02	≥ 6	≥ 6
Dimensional stability	EN ISO 23999	≤ 0.10%	≤ 0.10%
Chemical resistance	EN ISO 26987	Not affected (0)	Not affected (0)
Underfloor heating		Suitable	Suitable
ENVIRONMENTAL PERFORMANCES			
Total VOC emissions	ISO 16000-9	≤ 100 µg/m ³ (after 28 days)	≤ 100 µg/m ³ (after 28 days)
COLOURS			
		18	18

The above information is subject to modification for the benefit of further improvement. (06/19). *For information - not binding.

Customs Tariff: 4820500000

(1) Please note that slip resistance may be impacted by usage and cleaning operations.

According to the European Regulation N° 305/2011 for CE Marking, the Declarations of Performance are available on our website www.tarkett.com

Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for these instructions.



References	NCS No.	Welding Rod No.	LRV %
000	S 3020-Y10R	1287 432	33.18
001	S 4020-Y20R	1287 153	24.37
002	S 5020-Y20R	1287 477	18.14
003	S 5020-Y30R	1294 429	13.85
004	S 3005-Y20R	1287 501	37.72
005	S 3005-Y20R	1291 839	32.93

References	NCS No.	Welding Rod No.	LRV%
006	S 4010-Y30R	1287 560	23.53
007	S 6005-Y20R	1287 556	15.15
009	S 4005-Y50R	1287 591	35.97
011	S 5502-Y	1287 308	16.38
012	S 2005-Y30R	1287 402	41.80
014	S 4010-Y10R	1287 737	31.57

References	NCS No.	Welding Rod No.	LRV %
016	S 2005-Y50R	1287 805	42.36
017	S 4502-R	1287 730	27.02
018	S 5502-Y	1287 525	17.81
087	S 3502-Y	1287 532	32.34
088	S 4005-Y50R	1291 847	28.70
090	S 2502-Y	1287 290	42.45