


# marble fusion WFB

<b>CONSTRUCTION</b>	ituft 1/12" loop tipsheared	<b>PERMANENTLY ANTISTATIC</b>	ISO 6356
<b>STRUCTURE</b>	ituft 1/12" bouclé tipsheared	<b>ANTISTATIQUE PERMANENT</b>	< tbc kV
<b>STRUKTUR</b>	ituft 1/12" Tipsheared-Schlinge	<b>PERMANENT ANTISTATISCH</b>	
<b>STRUCTUUR</b>	ituft 1/12" lussenpool tipsheared	<b>PERMANENT ANTISTATISCH</b>	
<b>PILE MATERIAL</b>	100% PA 6 IMPREL® Solution Dyed	<b>IMPACT NOISE RATING</b>	ISO 140-8
<b>COMPOSITION DU VELOURS</b>		<b>ISOLATION PHONIQUE</b>	26 dB ΔLw
<b>POLMATERIAL</b>		<b>TRITTSCHALLVERBESSERUNG</b>	
<b>POOLMATERIAAL</b>		<b>GELUIDSISOLATIE</b>	
<b>PRIMARY BACKING</b>	Non woven PES	<b>SOUND ABSORPTION</b>	ISO 354
<b>SUPPORT</b>	PES non tissé	<b>ABSORPTION PHONIQUE</b>	0,25 Clw
<b>TRÄGERMATERIAL</b>	PES Vlies	<b>SCHALLABSORPTIONSGRAD</b>	
<b>TUFTDOEK</b>	PES Vilt	<b>THERMAL RESISTANCE</b>	ISO 8302
<b>SECONDARY BACKING</b>	Twinback	<b>RÉSISTANCE THERMIQUE</b>	0,11 m² K/W
<b>DOSSIER</b>		<b>WÄRMEDURCHLASSWIDERSTAND</b>	
<b>RÜCKEN</b>		<b>WARMTEDOORLAATWEERSTAND</b>	
<b>TAPIJTRUG</b>		<b>FASTNESS TO LIGHT</b>	ISO 105-B02
<b>PILE WEIGHT</b>	Ca. 800 gr/m²	<b>SOLIDITÉ A LA LUMIÈRE</b>	≥ 7
<b>POIDS DU VELOURS</b>		<b>LICHTECHTHEIT</b>	
<b>POLEINSATZGEWICHT</b>		<b>LICHTECHTHEID</b>	
<b>POOLGEWICHT</b>		<b>COLOUR FASTNESS TO WATER</b>	EN ISO 105-E01
<b>TOTAL WEIGHT</b>	Ca. 2.400 gr/m²	<b>SOLIDITÉ À L'EAU</b>	≥ 4-5
<b>POIDS TOTAL</b>		<b>WASSERECHTHEIT</b>	
<b>GESAMTGEWICHT</b>		<b>WATERECHTHEID</b>	
<b>TOTAAL GEWICHT</b>		<b>FIRE RESISTANCE</b>	EN 13501-1
<b>PILE HEIGHT</b>	Ca. 3,6-5,2 mm	<b>COMPORTEMENT AU FEU</b>	Cfl-s1
<b>EPAISSEUR DU VELOURS</b>		<b>BRENNVERHALTEN</b>	
<b>POLHÖHE</b>		<b>BRANDGEDRAG</b>	
<b>POOLHOOGTE</b>		<b>RUBBING FASTNESS</b>	EN ISO 105-X12
<b>TOTAL HEIGHT</b>	Ca. 7,7-9,3 mm	<b>SOLIDITÉ AU FROTTEMENT</b>	≥ 4
<b>EPAISSEUR TOTAL</b>		<b>REIBECHTHEIT</b>	
<b>GESAMTHÖHE</b>		<b>WRIJFECHTHEID</b>	
<b>TOTALE DIKTE</b>		<b>NUMBER OF COLOURS</b>	9
<b>TUFT DENSITY</b>	Ca. 282 000/m²	<b>NOMBRES DE COULEURS</b>	
<b>NOMBRES DE POINTS</b>		<b>ANZAHL FARBEN</b>	
<b>NOPPENZAHL</b>		<b>AANTAL KLEUREN</b>	
<b>AANTAL PUNTEN</b>		<b>WIDTH</b>	EN ISO 3018
<b>PILE DENSITY</b>	Ca. 0,122 g/cm³	<b>LARGEUR</b>	ca. 400 cm
<b>DENSITÉ DU VELOURS</b>		<b>BREITE</b>	
<b>POLROHDICHTE</b>		<b>BREEDTE</b>	
<b>POOLDICHTHEID</b>			
<b>CLASSIFICATION</b>	EN 1307		
<b>CLASSEMENT</b>	32 - LC2		
<b>KLASSIFIKATION</b>			
<b>CLASSIFICATIE</b>			
<b>CASTOR CHAIR SUITABILITY</b>	EN 985		
<b>CHAISE À ROULETTES</b>	A: intensive use		
<b>STUHLROLLENEIGNUNG</b>			
<b>ROLSTOELGESCHIKTHEID</b>			
<b>STAIR SUITABILITY</b>	EN 1963		
<b>ESCALIERS</b>	A: intensive use		
<b>TREPPENEIGNUNG</b>			
<b>TRAPPENGESCHIKTHEID</b>			



EN14041
<b>CE</b>
21
Balta Industries - Kanegem- straat 15 - BE 8700 Tielt
<b>DOP: 1011#IEOACL</b>
Textile Floor Covering EN1307 Notified body 2401
www.baltamediabank.com

arc edition


# marble fusion WFB




▲ 35



▲ 47




▲ 96



▲ 95




▲ 90



▲ 27



▲ 77



▲ 97



▲ 98